
BRICKMAX AM

Product:	A high purity manganese oxide powder for colouring of brick and tile and for use in refractory applications.
Appearance:	Extremely fine, brown powder
Particle size (typical):	<4% +45 μm
Specific surface area:	7.6 m^2/g typical (Malvern)
Absolute density:	4600 – 4900 kg/m^3
Tamped density:	1200 – 1600 kg/m^3
Moisture:	0.2% max
Mn as Mn_3O_4:	93.7 – 97.5%
Fe as Fe_2O_3:	Typically <4%

Typical values are provided in good faith as a guide and should not be taken as a specification.

The Company reserves the right to change the specification at any time.